


APPLICATION NOTES

AN 105



LAMINATION OF WINDSHIELDS (WINDSCREENS)



The lamination of windshields is the process of bonding a layer of special plastic film between two layers of glass. The plastic film is a safety barrier should the glass be broken in an accident.

The process requires that the plastic be inserted between the two layers of glass and then heated in a warm air oven to about 65°C (150°F). This critical temperature has to occur at the interface between the glass and the plastic film. The only way to measure this temperature is to use a non-contact infrared thermometer at the proper wavelength.

The best choice of instruments to use is a thermometer that operates at 3.4 microns. At this specific wavelength the glass is basically transparent which means it emits very little infrared energy. In addition at this wavelength the plastic film is totally opaque so that the infrared thermometer is basically measuring the temperature of the surface of the film which is the point at where the temperature is the most critical to assure proper bonding.

The instrument is installed at the exit of the oven and requires the use of a Peak-Picker to measure the windshields and not the spaces between the pieces of glass. In addition we suggest the use of an air purge to keep the lens clean. Gases from the plastic will coat the lens and cause errors in the indication.

Ircon can provide one of several instruments for this application. They include the Modline 3400, Modline 43 or the Maxline M3 series. These instruments are available with linear 4-20 mA outputs, alarms and digital indication. Call Ircon and request a demonstration on your line.

For further information contact Ircon at:

Phone: 847-967-5151
Phone: 800-323-7660 USA and Canada only
Fax : 847-647-0948

IRCON, INC.
7300 North Natchez Ave.
Niles, Illinois 60714 USA

AN 105 Part No. 010205 Rev. B
©1998 IRCON, INC. All Rights Reserved

Phone: (847) 967-5151
Toll Free: (800) 323-7660
Fax: (847) 647-0948
Web site: www.ircon.com

2M 10/96 Printed in USA

